

**AMENDMENT NO. 01 TO SLS 634 : 1984
SPECIFICATION FOR PLASTIC BUCKETS**

EXPLANATORY NOTE

This amendment is introduced a) to amend clause **4.2.5** to include number of measurements to be taken to determine thickness of the bottom of the bucket, b) to amend clause **4.6.3** to give the correct reference to ISO 4892 as it has been revised in 1994 and c) to amend test method for determination of colour fastness to water (clause **H.1** of Appendix **H**).

**AMENDMENT NO. 01 APPROVED ON 1995-11-23 TO SLS 634 : 1984
SRI LANKA STANDARD SPECIFICATION FOR PLASTIC BUCKETS**

Page 4

Clause 4.2.5

Delete the existing test in clause **4.2.5** and substitute the following:

“The thickness of any point of the bottom of the bucket shall be not less than 2 mm when measured at 20 randomly selected points.”

Page 5

Clause 4.6.3.1

In line 3 substitute “**5.1.3**” with “**Part 4**”.

Page 13

Appendix H

Clause H.1 PROCEDURE

Delete the first sentence and substitute the following:

“Cut a small piece of 50 mm square from a sheet of material to be tested (the thickness is of no importance) and place it in a 100 mm beaker.”