

**AMENDMENT NO. 1 APPROVED ON 2008.12.19
TO SLS 31 : 1988**

SPECIFICATION FOR GALVANIZED MILD STEEL BARBED WIRE

Clause 2

Delete the first line and substitute with the following:

SLS 978 : Tensile Testing of Metallic Materials

Clause 4.2.1

Delete “CS 76” and substitute with “SLS 978”

Clause 4.1.2.2

Delete the text and substitute with the following:

“The minimum mass of zinc coating per unit area when measured by the methods specified in CS 121, shall be 40 g/m^2 for wire of diameter 2.00 mm and 45 g/m^2 for wire of diameter 2.50 mm as laid down in SLS 139”.